



Advisory

May 2004

ADVISORY ON FASTENERS AND CONNECTORS FOR TREATED WOOD

Metal products in contact with pressure-treated wood must be corrosion resistant. Examples include flashing, termite shields, fasteners (e.g. nails, screws, and bolts), and all connecting hardware (e.g. joist hangers, straps, hinges, post anchors, and truss plates).

The International Residential Code, Section R319.3 states, "Fasteners for pressure-preservative treated wood shall be of hot-dipped galvanized steel, stainless steel, silicon bronze or copper. **Exception:** One-half inch (12.7mm) diameter or greater steel bolts."

Traditionally, the treated wood industry has recommended hot-dip galvanized or stainless steel fasteners and connectors for wood products treated with Chromated Copper Arsenate (CCA). Hot-dip galvanized or stainless steel fasteners and connectors continue to be recommended for use with alternative wood preservatives (e.g. Alkaline Copper Quat – ACQ – and Copper Azole), but additional clarification is needed to ensure adequate corrosion protection.

Type 304 or 316 stainless steel is recommended for maximum corrosion resistance in more severe exterior applications, such as swimming pools and saltwater exposure. Furthermore, stainless steel fasteners are generally required below grade for permanent wood foundations.

Hot-dip galvanized fasteners and connectors are generally acceptable for above-grade applications. Hot-dip galvanized *fasteners* should meet *ASTM A153*, with 2 ounces of zinc coating per square foot minimum. Hot-dip galvanized *connectors* should meet *ASTM A653*, Class G185 sheet with 1.85 ounces of zinc coating per square foot minimum. Fasteners and connectors used together should be of the same type (e.g. hot-dip nails with hot-dip joist hangers).

Do not use standard carbon-steel or aluminum products in direct contact with pressure-treated wood. Spacer materials or other physical barriers are recommended to prevent direct contact. In addition, electroplated galvanized metal products generally have a thinner layer of protection compared to hot-dip galvanized and are typically not accepted by the building codes for use in exterior applications.

Fasteners and connectors coated with proprietary anti-corrosion technologies (other than stainless steel or hot-dip galvanized) are also available for use with treated wood. Consult individual hardware manufacturers for specifics regarding the performance of their products with treated wood.

P.O. Box 641700 Kenner, LA 70064 • 504/443-4464 FAX: 504/443-6612

www.southernpine.com